947 IV was developed especially for printing presses using cartridges with integrated felt or foam rubber reservoir. The binding agent prevents the ink cartridge diaphragms from sticking.

Properties:

This ink dries very quick, provides an intense colour and is particularly economical.

Application:

We recommend 947 IV for marking painted and unpainted metals, rubber, wood as well as various plastics with light background. A suitability test should be carried out as too many different qualities are available to allow a reliable recommendation.

Drying time:

~10-25sec (metal)



Viscosity:

low viscosity, ~10-20sec (Ford 4mm cup)

Stamp material:

Rubber, metal or special photo polymers

Stamp pad material:

We recommend only cartridges with felt or foam rubber filler for 947 IV. On flexographic printing systems, use closed ink reservoirs.

Thinner/cleaner:

Thinner 425

Available standard sizes:

 $50ml/g \cdot 250ml/g \cdot 1000ml/g \cdot 5000ml/g$

Transparent



Opaque